



(19)

(11) Publication number: 06344362 A

Generated Document.

PATENT ABSTRACTS OF JAPAN

(21) Application number: 05140293

(51) Intl. Cl.: B29C 43/18 B29C 33/12 B29C 43/34

(22) Application date: 11.06.93

(30) Priority: (43) Date of application publication: 20.12.94 (84) Designated contracting states:	(71) Applicant: MITSUI PETROCHEM IND LTD (72) Inventor: KOBAYASHI TOSHIO WATARI MITSURU KIMURA TAKASHI (74) Representative:
---	---


(54) MANUFACTURE OF
COMPOSITE FOAM-MOLDED
PRODUCT

(57) Abstract:

PURPOSE: To obtain a light-weight, highly rigid composite foam-molded product by regulating top and bottom forces to have a specified mold space with the aid of a mold space adjusting material in a very short period of time and expanding a resin composition.

CONSTITUTION: A skin material A is set between a top and a bottom forces 1, 2. After keeping a specified space between the forces, a polypropylene resin composition containing a foaming agent, which has been melted at a predetermined temperature, is introduced into a space between the bottom force 2 and the skin material, 8. At the same time, the top force 1 is lowered down at a predetermined speed to clamp the forces until the forces have a predetermined space, and a base material layer, which has not yet been expanded, is integrated with the skin material 8

simultaneously with the shaping of a base material shape. In a period of 0.5 to 5 seconds, the top force 1 is elevated, and it is then lowered until a space L3 between the top and bottom forces 1, 2 is within a range satisfying a formula $-t_2+t_3 \times 1.1 \sim L_3$ $t_2+t_3 \times 2.0$ —with the aid of a mold space adjusting material 20' to expand the polypropylene resin composition. Thus, a foamed base material layer 14 composed of the polypropylene resin composition is cooled and hardened under the pressurized condition while the mold space adjusting material 20' is being kept in a set state.



COPYRIGHT: (C)1994,JPO